

EXPERIMENTAL STUDY ON HIGH PERFORMANCE CONCRETE USING DIFFERENT TYPES OF AGGREGATE

Mr. A. Magesh* and Mr.S.Udaya Kumar*

**Assistant Professor of Civil Engineering, New Prince Shri Bahvani College of Engineering and Technology, Chennai, Tamilnadu, India*

ABSTRACT- A new generation of concrete, High performance of concrete has been developed of its outstanding strength durability performance shows a very promising future in construction application in this paper several possibilities are examined for reducing the price of producing high performance concrete and to minimize the ability of normal concrete. The following types of coarse aggregate were used to produce the concrete; secondary aggregate; marble; light weight aggregate (pumice) and natural mineral (gravel). The concrete contain a highly effective Super plasticizer and metakoline. Mechanical properties and water absorption sharply increased during early stage approaching asymptotic values, depending on design strength codes. Results of 28 days of curing light weight aggregate gives the high mechanical properties. When estimated with the conventional concrete. These experimental results demonstrate that the light weight aggregate strongly influences the mechanical and durability properties without basic properties of concrete.

Keywords: High performance concrete, aggregate type, workability, durability, compressive strength, tensile strength.

1. INTRODUCTION

India being a place for multiple biodiversity holds a highly dynamic range of topography, hence having various kinds of rock materials depending upon the area of residing. Various new construction methods have come up in the past decade to make use of the resources cost efficiently without causing any distress and to make people live in safe zone. This safe zone majorly consists of keeping the

building as high performance building.

Theoretical studies are available to determine strength of different building components. But a very few studies are available which deal with experimental investigation. The various rock materials end up in giving variety of coarse aggregates; Aggregate characteristics as well as properties of cement paste and Interfacial Transition Zone (ITZ) govern the strength and durability of concrete with the improvement in properties of cement matrix and ITZ by the use of mineral and chemical admixtures in HPC.

HPC is a concrete mixture, which possess high durability and high strength when compared to conventional concrete. The term 'High performance' is somewhat pretentious because the essential feature of this concrete is that it's ingredients and proportions are specifically chosen so as to have particularly appropriate properties for the expected use of the structure such as high strength and low permeability. Hence HPC is not a special type of concrete. It comprises of the same materials as that of the conventional cement concrete. The use of some mineral and chemical admixtures like silica fume and super plasticizer enhance the strength, durability and workability qualities to a very high extent.

T.Subulakshmi et al investigation made on the mechanical properties of High performance concrete made with quarry dust material. This paper presents the results of a study to use quarry dust in concrete as a partial replacement of sand. The strength characteristics such as compressive strength and flexural strength were investigated to find the optimum replacement of quarry dust. The

mechanical properties of HPC with quarry dust at the replacement levels of 0,50,100% were studied at 3,7,14,28 and 60 days curing. Quarry dust plays a vital role in improving the strength of the concrete.

K.S. Kulkarni et al studied the use of HPC has been used extensively throughout the world, predominately in the high rise buildings, bridges, tunnels etc. The first fire that occurred in a HPC structure was in the channel tunnel fire. From different studies in progress in several countries, it is clear that the fire resistance of HPC does not seem to be as good as that of ordinary concrete. This experimental work regarding the physical characteristics, mechanical properties of partial micro cement based HPC subjected to elevated temperatures.

Saied Ahmed Al. Sheikh studied the experimental investigation in to the effects of high temperature on the residual compressive and tensile strengths for HPC made with ordinary portland cement are presented. The results showed that the compressive and tensile strengths, pulse velocity and rebound number were decreased with the increase in exposed temperature. The weight loss from concrete increased non- linearly with the maximum exposed temperature. Sudden cooling caused reduction in concrete strength.

II. MATERIALS

OPC confirming to IS 12269: 1987 (Specification for 53 grade OPC), fine aggregates, coarse aggregates and potable water were used for the control OPC concrete specimens. The HPC was obtained by mixing calculated quantities of cement, fine aggregate, coarse aggregate and super plasticizer. River sand available in Chennai was used as fine aggregates and tested as per IS 2386: Part I: 1963 (Methods of test for aggregates for concrete). In this investigation locally available crushing natural stone rock as (Gray Gravel), wastage material from the demolished buildings as Secondary aggregates (Brick debris), crushed Marbles, Light weight aggregate all these aggregate as maximum size of 20mm was used and

characterization tests were carried out as per IS

Specific Gravity of Fine aggregate – 2.60			
Sieve size	Weight retained (gms)	Cumulative (%) passed	Zone
4.75 mm	21	98.95	1, 2, 3, 4
2.36 mm	109	93.5	1, 2, 3, 4
1.18 mm	353	75.85	1, 2, 3
600 micron	861.5	32.77	1, 2, 3
300micron	510.5	7.25	1
150 micron	122.5	1.125	1, 2, 3, 4
Pan	22.59	0	Nil

2386: Part I: 1963 (Methods of test for aggregates for concrete)

A. Ordinary Portland cement (OPC)

The basic properties of 53 grade OPC such as consistency, initial setting time, final setting time and specific gravity were given in Table 1. as per IS 4031- methods of physical test for hydraulic cement.

TABLE 1 PROPERTIES OF 53 GRADE ORDINARY PORTLAND CEMENT

TEST DETAILS	OBTAINED VALUE	CODAL REQUIREMENT AS PER IS 4031-1998
Fineness of cement	7%	
Consistency	27%	
Initial setting time	30 min	Not less than 30 min
Final setting time	540 min	Not more than 600 min
Specific gravity	2.91	

B. River sand

River sand obtained from local source was used as a fine aggregate. The properties of fine aggregate are tabulated in Table 3.2 the test was carried out as per IS 383- specification for fine aggregate from natural source for concrete.

TABLE 3.2 PROPERTIES OF FINE AGGREGATE

From table 1 the soil sample comes under Zone 1 with ref to table 2.

C. Aggregates

In the present investigation, locally available different types of aggregate such as Gravel, debris aggregate, Light weight, Marble are obtained from the local source was used. The properties of coarse aggregate are given in Table 3.as per IS 383-Specification for coarse and fine aggregate from natural source for concrete.

TABLE 3 PROPERTIES OF COARSE AGGREGATE

SI NO	AGGREGATES TYPE	SPECIFIC GRAVITY
1	Gravel	2.80
2	Secondary	2.62
3	Light weight	2.33
4	Marble	2.72

D. Super Plasticizer

In order to improve the workability of fresh concrete, Conplast SP 430 type of super plasticizer was used.

III PREPARATION OF TEST SPECIMENS

Cement, sand and aggregate are weighted separately and mixed together in a dry manner. The amount of water and Super plasticier are calculated also as per Indian standard are measured, mixed together thoroughly and this emulsified water should be used for the preparation of concrete. The mixing

was done by the hand and precautions were taken to ensure the uniform mixing of ingredients.

The test specimen of size 150 x 150 x150 mm were cast in a mould made of 4mm thick sheet for all concrete specimen. The specimens were demoulded after 24 hours of casting and cured in water for 7, 28 days. To achieve the initial and final stage strength curing is carried out which helps us to improve the strength of concrete it will be done as per Indian standard.

III. EXPERIMENTAL INVESTIGATIONS

High performance concrete is not a special type of concrete. It comprises of the same materials as that of the conventional cement concrete. The use of some mineral and chemical admixtures like Silica fume and Super plasticizer enhance the strength, durability and workability qualities to a very high extent in control specimens. To reduce the natural minerals different types of aggregate are used. To investigate that those aggregate types in concrete should increase the strength and durability of

concrete structure. The

following strength and durability studies were conducted to assess the performance of high performance concrete.

Compressive strength tests

The compressive strength tests are carried out as per IS 516-1968 (methods of tests for strength of concrete) to find the influence of high performance concrete on the compressive strength development of cement concrete. The specimens of size 150mm cube were casted with the various types of aggregate. Totally 30 specimens were casted. The test was carried out at the ages of 7 and 28 days tests results are compared with control concrete specimens.

Splitting tensile strength test

The objective of this test is to assess the influence of various types of aggregate addition on tensile strength development of high performance concrete. The test was carried out as per IS 5816-1999 (Splitting tensile strength of concrete – Method of test). A total of 15 cylinder specimens of size 100mm diameters and 200mm length were casted with different types of aggregate. The tests was conducted at the age of 7 and 28 days curing period for both control and other types of aggregate used concrete.

Water absorption tests

The specimens made with ordinary cement mortar will absorb water to a certain extent. The important parameter that influences the rate of water absorption is the degree of hydration and water-cement ratio. The increases in degree of hydration and decrease in water-cement ratio will certainly reduce the rate of water absorption. In addition of super plasticizer the larger pores are filled with water reducing agent. This feature reduces water absorption. The objectives of this test is to study the water absorption properties due to replacement of different types of aggregate.

Rapid chloride penetration test

This test method is assessed to find out the penetration depth of chloride ingresses to the concrete surface as per ASTM-C-1202 (standard test method for electrical indication of concrete's ability to resist chloride ion penetration) the performance based found by monitoring the amount of electrical current passed through 50mm thick slices of 100mm nominal diameter coarse during a 6 hrs period. Totally 8 concrete cylinder of size 100mm x 200mm were cast and 50mm slices were was cut with a help of concrete angle cutter. Totally three different combination were cast and three cylinders were cast in each categories. This test used to assesses. The resistance of concrete against chloride ingresses is conducted as per ASTM-C-1202.

IV RESULT & DISCUSSION

The results of the experimental program followed for the determination of strength, durability of Concrete cubes and cylinder are discussed with the results

Results for Compressive Strength




Figure 1 Comparison of Compressive strength for Control Concrete and different types of aggregate

Figure 1 shows Comparison of Compressive strength for Control Concrete and different types of aggregate. In general mix ratio are designed irrespective of types of aggregate used in concrete. In initial stage control concrete offered improved strength of 37 MPa similarly the light weight aggregate (i.e. Pumice) also gives strength of 36 MPa compared to the other types of aggregate such as 16, 15, 31 MPa. Then the gravel gives the moderate strength in the initial stages. It can be concluded that irrespective of type of aggregate 28 days test results revealed similar Compressive strength for Gravel, Pumice, Marble and secondary in concrete. Whereas marginally improved Compressive strength of the order of 30% for Control and Pumice mortar in different mix ratio which may be due to improved hydration.

Result For Split Tensile Strength




Figure 2 Comparison of Split tensile strength for Control mortar and different types of aggregate

Figure 2 shows the Comparison of Split tensile strength for Control mortar and different types of aggregate. In general mix ratio are designed irrespective of types of aggregate used in concrete. In initial stage control concrete offered improved strength of 3.4 MPa similarly the light weight aggregate (i.e. Pumice) also gives strength of 3.7 MPa compared to the other types of aggregate such as 0.7, 0.6, 2.9 MPa. Then the gravel gives the moderate strength in the initial stages. It can be concluded that irrespective of type of aggregate 28 days test results revealed similar Compressive strength for Gravel, Pumice, Marble and secondary in concrete. Whereas marginally improved Compressive strength of the order of 30% for Control and Pumice mortar in different mix ratio which may be due to improved hydration.

Water Absorption Test Results




Figure 3 Behavior of Water absorption for types of aggregate Vs Water absorption (%)

Figure 3 shows the Behavior of Water absorption for types of aggregate Vs Water

absorption (%). In this test 100mm concrete cubes are casted with different types of aggregate. Whereas water absorption depth of concrete also will differ irrespective to type of the aggregate. Here three specimens were casted for each type of aggregate. Generally Control will have more water absorption(%) similarly the Gravel. It can be concluded that the Marble and Pumice will have lesser depth of water absorption.

Rapid Chloride Penetration Test

TABLE 4 CHLORIDE ION PENETRABILITY BASED ON CHARGE PASSED

Charge Passed (Coulombs)	Chloride Ion Penetrability
>4000	High
2000-4000	Moderate
1000-2000	Low
100-1000	Very Low
<100	Negligible

The value of charge passed through the concrete during the period of 6 hours was calculated as per code and is shown in Table 4.




Figure.5 Comparison of Charged passed per milli ampere in different types of aggregate

CONCLUSION

This paper presents experimental study on high performance concrete using different types of aggregates. The following conclusions are derived based on the analysis.

- Compressive strength of 36 MPa was achieved at the age of 7day for high performance concrete using Light weight aggregate (i.e. Pumice). The strength improvement is similar to the Control Concrete.
 - At the final stage for curing Pumice and Gravel will give the expected outcome strength in the High Performance Concrete.
 - The observation of Compressive strength is in close agreement with the expected theoretical strength attainment values for M55 Concrete
 - In Split tensile test Pumice will give a higher tensile strength of 9.2 MPa. Gravel will also offer similar strength.
 - The bond strength development of using Pumice in high performance concrete is comparable with the expected values for control concrete.
 - Water absorption percentage obtained for pumice is nominal but the subsequent strength reduction needs further study.
 - The durability up to 40 % improvement in light weight aggregate using high performance concrete.
 - Water absorption and Rapid chloride penetration test results revealed an adequate durability property for high performance concrete using pumice aggregate
 - It can be concluded that the strength and durability properties of high performance concrete using different types of aggregate is improved by adequate modification in mixing and curing methods and by appropriate proportion.
- [2] Jamkar, S.S. & Rae, C.B.K. (2004). Index of aggregate particle shape and texture of coarse aggregate as a parameter for concrete mix proportioning. *Cement and Concrete Research* 34, No.11, 2021-2027.
- [3] Jeddah, M.S., Zitouni, S. & Belaabes, S. (2010). Effect of content and particle size distribution of coarse aggregate on compressive strength of concrete. *Construction and Building materials* 24, No. 4, 505-512.
- [4] Kwan, A.K.H. & Fung, W.W.S. (2009). Packing density measurement and modeling of fine aggregate and mortar. *Cement and Concrete Composites* 31, No.6, 349-357.
- [5] Kwan, A.K.H. & Mora, C.F. (2001). Effects of various shape parameters on packing of aggregate particles. *Magazine of Concrete Research* 53, No.2, 91-100. Lees, G. (1970). The rational design of aggregate grading for dense asphaltic compositions. *Proceedings of Asphalt paving Technologies* 39: 60-90.
- [6] Neville, A.M. *Properties of concrete*. 4th ed. Pearson, India, 2010.
- [7] Sobolev, K. & Amirjanov, A (2010). Application of Genetic Algorithm for modeling of dense packing of concrete aggregates. *Construction and Building materials* 24, No.8, 1449-1455.

REFERENCES

[[1] Donza, H., Cabrera, O. & Irassar, E.F. (2002). High-strength concrete with different fine aggregate. *Cement and Concrete Research* 32, No.11, 1755-1761.

IJRDO